

Informationen

zur Zertifizierung nach Baustoffklasse EN 13501-1:2018

Stoff • mailand

Farb.-Nr.

209.xx

Prüfzeugnis: **K102/2024**

Bestätigung Die Firma erfal bestätigt, dass dieser Qualität das Zertifikat K102/2024 zugrunde liegt.



Jörg Erler
Geschäftsführer

erfal steht für Qualität Made in Germany.

Um eine lange Lebensdauer unter Wahrung der ursprünglichen Produkteigenschaften zu gewährleisten, sollten Sie die mitgelieferten Pflege- und Reinigungsmöglichkeiten unbedingt beachten.

Bei Fragen zur Pflege unserer Stoffe melden Sie sich bitte bei:

erfal GmbH & Co. KG
Gewerbering 8
D - 08223 Falkenstein

Fon +49 (0) 3745 750 0
Fax +49 (0) 3745 750 299
info@erfal.de

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA
VAT No. LV 43603022749
Dobeles iela 41, Jelgava, LV-3001, Latvia
Phone +371 63010605 * E-mail meka@e-koks.lv * Web www.e-koks.lv



Classification of reaction to fire in accordance with EN 13501-1:2018

Issue number: K102/2024

Date of issue: 22.08.2024.

Sponsor: Junkers & Müllers GmbH.

Address: Bolksbuscher Str. 27, 41239 Mönchengladbach, Germany.

Reg. No. HRB 3591, Mönchengladbach.

Manufacturer and owner of classification report: Junkers & Müllers GmbH.

Prepared by: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*).

Test performed at: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*), “Pienavas katlu māja”, Pienava, Džūkstes pagasts, Tukuma novads, LV-3147, Latvia (*“Pienava heat plant”, Pienava, Džūkste parish, Tukums region, LV-3147, Latvia*).

Product name: Pleated fabrics JM Collection JM PEARL FR.

The laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316. The laboratory is a notified body with reg. No. NB 2040 under construction product regulation No. 305/2011.

The classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, except with the prior written approval of the Forest and Wood Products Research and Development Institute

1. Introduction

This classification report defines the reaction to fire classification assigned to Pleated fabrics JM Collection JM PEARL FR in accordance with the procedures given in EN 13501-1:2018.

2. Details of classified product

2.1. General

Polymer coated woven fabric made of polyester Pleated fabrics JM Collection JM PEARL FR is defined as sun-shading fabric for pleated-blind. There is no harmonised European technical specification standard available describing this product.

2.2. Product description

- Product name: Pleated fabrics JM Collection JM PEARL FR.
- Product variables:
 - CRUSH PEARL FR: thickness approx. 0.3 mm, surface mass/area approx. 105 g/m²;
 - SCALA PEARL FR: thickness approx. 0.2 mm, surface mass/area approx. 100 g/m².
- Product description: woven polyester fabric with polymer coating.
- Manufacturer: Junkers & Müllers GmbH.
- Materials used for manufacturing:
 - fabric made of 100 % polyester;
 - polymer coating with flame-retardant additives;
 - crushed and pleated fabric with pearl effect on the back side (CRUSH PEARL FR) and pleated (SCALA PEARL FR);
- Colours of CRUSH PEARL FR: white, red and deep grey;
- Colour of SCALA PEARL FR: asphalt.

3. Test reports and test results in support of classification

3.1. Specific conditions

Not applicable.

3.2. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Junkers & Müllers GmbH	9712-1/2024	EN 13823:2020+A1:2022
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Junkers & Müllers GmbH	9712-2/2024	EN ISO 11925-2:2020

3.3. Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2020+A1:2022	<i>FIGRA</i> _{0,2MJ} (W/s)	7	Threshold not reached	(-)
	<i>FIGRA</i> _{0,4MJ} (W/s)		Threshold not reached	(-)
	<i>THR</i> _{600s} (MJ)		0.1	(-)
	<i>LFS</i> < edge of specimen		yes	Compliant
	<i>SMOGRA</i> (m ² /s ²)		Threshold not reached	(-)
	<i>TSP</i> _{600s} (m ²)		2	(-)
	Flaming droplets <10s Flaming droplets >10s		no no	Compliant Compliant
EN ISO 11925-2:2020 Exposure time 30 s. Test duration 60 s.	Flame spread (Fs) ≤ 150mm	16	yes	Compliant
	Ignition of filter paper		no	Compliant
	Flaming droplets/particles		no	Compliant
(-) not applicable				

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2. Classification

Pleated fabrics JM Collection JM PEARL FR in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

Reaction to fire classification: B-s1, d0

4.3. Field of application

4.3.1 This classification is valid for the following product end-use applications:

The product primary is intended to be used as sun-shading fabric (pleated-blind).

4.3.2. This classification is also valid for the following product parameters:

- valid only for thickness as tested;
- valid only for product composition as tested;
- valid only for surface mass/area as tested;
- product performance determined without substrates mounted as free-standing installation with calcium silicate backing. Classification valid for product mounting as ventilated, free-standing or suspended installations;
- product tested without joints;
- valid for both sides of the fabric;
- valid for all colours.

5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.

Prepared by



E. Bukšāns

(signature and name)

Reviewed by



K. Būmanis

(signature and name)

THIS DOCUMENT IS SIGNED BY SECURE ELECTRONIC SIGNATURE AND CONTAINS A TIME STAMP
(Signature validity can be checked: <https://www.eparaksts.lv/en>)